

手工藝品應用接著劑

UV glue for handcraft application

產品特性 / Feature

<p>玻璃和水晶 接著 Glass and crystal bonding</p>	<ul style="list-style-type: none"> ◆ 通過嚴苛的高、低溫環測及長期25°C泡水試驗 Pass severe high/low temperature experiment tests and 25°C long-term water immersion test ◆ 通過長時間日曬雨淋測試 Pass long-term outdoor weather-proof test ◆ 經過老化測試後不會產生黃變現象 Good yellowing resistance after aging test ◆ 適合傢俱、工藝品、花瓶缸、衛浴用具、光學玻璃產業接著 Suitable for furniture, crafts, vases, sanitary appliances, and optical glass bonding 	
<p>塑膠接著 Plastics bonding</p>	<ul style="list-style-type: none"> ◆ 高透明度、高接著強度 High transparency, high adhesion strength ◆ 具有良好延伸性及耐震特性 Good extensibility and shock resistance ◆ 接著工件做破壞測試時，可達到材破而不脫膠 Cured resin can achieve substrate failure without adhesive failure in bonding strength test. ◆ 適合電子、藝品類接著 Suitable for electronics and arts bonding 	
<p>金屬和玻璃 接著 Metals and glass bonding</p>	<ul style="list-style-type: none"> ◆ 膠體固化後韌度高 Cured glue has high toughness ◆ 具有良好延伸性及耐震特性 Good extensibility and shock resistance ◆ 經過高低溫循環測試後，不會產生脫膠及龜裂現象 No adhesive failure and crack after high/low temperature experiment tests ◆ 傢俱、工藝品、電子零件接著 Suitable for furniture, crafts, and electronic devices bonding 	

玻璃和水晶接著 Glass and crystal bonding

產品編號 Product No.	外觀 Appearance	黏度, cps Viscosity, cps	硬化條件, mJ/cm^2 Curing condition, mJ/cm^2	硬度 Hardness, Shore D	接著強度 kg/cm^2 Tensile strength, kg/cm^2	耐熱範圍, °C Working Temperature range, °C
GA004	透明液體 Colorless liquid	16,000~26,000	1,500	70	81	-20~100
GA006	透明液體 Colorless liquid	6,400~9,600	1,500	71	72	-20~100
GA024	透明液體 Colorless liquid	2,050~3,150	1,500	70	84	-20~100

以上數據僅供參考，詳情請查閱技術資料。
Please refer to the Technical Data Sheet for detailed information.

PMMA / PC / ABS接著 PMMA / PC / ABS bonding

產品編號 Product No.	外觀 Appearance	黏度, cps Viscosity, cps	硬化條件, mJ/cm^2 Curing condition, mJ/cm^2	硬度 Hardness, Shore D	接著強度 kg/cm^2 Tensile strength, kg/cm^2	耐熱範圍, °C Working Temperature range, °C
GP135	透明液體 Colorless liquid	3,200~4,800	1,500	62	62	-20~100
GP575	透明微黃色液體 Light yellow liquid	650~1,050	1,500	54	74	-20~100
GN156	透明液體 Colorless liquid	5~15	1,500	64	59	-20~100

以上數據僅供參考，詳情請查閱技術資料。
Please refer to the Technical Data Sheet for detailed information.

金屬和玻璃接著 Metals and glass bonding

產品編號 Product No.	外觀 Appearance	黏度, cps Viscosity, cps	硬化條件, mJ/cm^2 Curing condition, mJ/cm^2	硬度 Hardness, Shore D	接著強度 kg/cm^2 Tensile strength, kg/cm^2	耐熱範圍, °C Working Temperature range, °C
GM005	透明液體 Colorless liquid	5,000~7,500	1,500	63	198	-20~100
GM300	透明液體 Colorless liquid	800~1,300	1,500	64	202	-20~100
GM220	透明液體 Colorless liquid	300~460	1,500	51	164	-20~100

以上數據僅供參考，詳情請查閱技術資料。
Please refer to the Technical Data Sheet for detailed information.